

---

---

**Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials —**

**Part 1:  
Infrared measurement methods**

*Essais des matières premières pour produits réfractaires — Dosage du soufre dans les matières premières non oxydantes sous forme de poudre et de granulés —*

*Partie 1: Méthodes d'essai par infrarouge*



This document is a preview generated by EMS



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

|  | Page      |
|--|-----------|
| <b>Foreword</b> .....  | <b>iv</b> |
| <b>1 Scope</b> .....   | <b>1</b>  |
| <b>2 Principle</b> .....   | <b>1</b>  |
| <b>3 Apparatus</b> .....   | <b>1</b>  |
| <b>4 Reagents</b> .....  | <b>2</b>  |
| <b>5 Sampling and sample preparation</b> .....   | <b>2</b>  |
| <b>6 Calibration</b> .....   | <b>2</b>  |
| <b>7 Performance</b> .....   | <b>2</b>  |
| 7.1 Preparation of analysis.....   | 2         |
| 7.2 Determination of blank value.....  | 3         |
| 7.3 Determination of sulfur content.....   | 3         |
| <b>8 Calculation and report of the results</b> .....   | <b>3</b>  |
| <b>9 Precision</b> .....   | <b>3</b>  |
| 9.1 Repeatability.....   | 3         |
| 9.2 Reproducibility.....   | 3         |
| <b>10 Test report</b> .....  | <b>3</b>  |
| <b>Annex A (informative) Results of the round-robin test</b> .....                                     | <b>5</b>  |
| <b>Annex B (informative) Information regarding the validation of the uncertainty of the mean value</b> | <b>7</b>  |
| <b>Annex C (informative) Commercial Certified Reference Materials (CRM)</b> .....                      | <b>8</b>  |
| <b>Bibliography</b> .....  | <b>9</b>  |

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14720-1 was prepared by Technical Committee ISO/TC 33, *Refractories*.

ISO 14720 consists of the following parts, under the general title *Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials*:

- *Part 1: Infrared measurement methods*
- *Part 2: Inductively coupled plasma optical emission spectrometry (ICP/OES) or ion chromatography after burning in an oxygen flow*

# Testing of ceramic raw and basic materials — Determination of sulfur in powders and granules of non-oxidic ceramic raw and basic materials —

## Part 1: Infrared measurement methods

### 1 Scope

This part of ISO 14720 defines a method for the determination of sulfur in powdered and granular non-oxidic ceramic raw materials and materials, such as silicon carbides, silicon nitrides, graphites, carbon blacks, cokes, carbon powders. If proved by the recovery rate, this method can also be applied for other non-metallic powdered and granular materials, e.g. silicon dioxide.

This part of ISO 14720 is applicable for materials with mass fractions of sulfur from 0,005 % to 2 %.

This part of ISO 14720 can also be applied for materials with higher mass fractions of sulfur after verification of the particular case.

### 2 Principle

The sample and added combustion accelerators (mostly tungsten- or iron-granules) are heated in an inductive furnace under oxygen atmosphere. The high-frequency field of the furnace couples with electrically conductive components of sample and combustion accelerators. The sample is heated to temperatures above 1 800 °C and the total sulfur content of the sample is released as sulfur dioxide. The reaction gas is transferred to the infrared absorption cell of the analyser. The molecular absorption of sulfur dioxide is measured by using a narrow-band optical filter which is translucent for the wavelength of the characteristic infrared absorption of sulfur dioxide. The mass fraction of sulfur dioxide in the reaction gas is proportional to peak-height and peak-area, respectively, of the transient absorption signal. The mass fraction of sulfur in the sample is calculated by using a calibration function established by suitable calibration standards measured under comparable conditions.

### 3 Apparatus

#### 3.1 Device with induction furnace or alternatively resistance furnace and infrared cell.

**NOTE** The correctness of the analysis result can be proved by using matrix-analogous reference materials or by comparing with an independent alternative test method. If determining mass fractions below 100 mg/kg, it has to be considered that some analytical devices may deliver incorrect results.

#### 3.2 Analytical balance, capable of reading to the nearest 0,01 mg.

#### 3.3 Ceramic crucible, e.g. mullite or alumina.

#### 3.4 Crucible lid with hole, e.g. mullite or alumina.